

PRODUCT DATA SHEET

Product Category	Product Name	Grade
Polymers	POLYETHYLENE – LDPE	2420 H

Property	Value	Unit	Test Method
Mass Density (23 °C)	0.924	g/cm ³	ISO1183
Melt Flow Rate (190°C /2.16kg)	2.0	g/10min	ISO1133
Melting point	112	°C	ISO11357
Vicat softening temperature, A/50	95	°C	ISO306
Tensile Modulus of Elasticity	270	MPa	ISO527
Stress at Yield	11	MPa	ISO527
Shore D hardness	48	–	ISO868
Max. tensile strength MD	23	MPa	ISO527
Max. tensile strength TD	21	MPa	ISO527
Maximum elongation MD	580	%	ISO527
Maximum elongation TD	700	%	ISO527
Dart Drop Impact	110	g	ASTM D1709
Gloss (60°)	120	–	ASTM D2457
Haze (40µm film)	6.5	%	ASTM D1003

Application	Bags & Pouches, Film Shrink, Film Blown Film, Cast Film.
Characteristics	Good Heat Seal, Optical, Good Processability.
Packaging	25 Kg plastic bag